
HOSTAFORM® S 9363 XAP2™ | POM | Impact Modified

Description

Hostaform® acetal copolymer grade S 9363 XAP2™ is an impact modified grade for demanding applications. Hostaform® S 9363 XAP2™ provides good impact strength while improving modulus and weld line strength over standard impact modified grades such as Hostaform® S 9063, and also exhibits exceptional low emission performance meeting or exceeding the requirements of many automotive markets.


Chemical abbreviation according to ISO 1043-1: POM-HI

Physical properties	Value	Unit	Test Standard
Density	1380	kg/m ³	ISO 1183
Melt volume rate (MVR)	5.5	cm ³ /10min	ISO 1133
MVR test temperature	190	°C	ISO 1133
MVR test load	2.16	kg	ISO 1133
Mold shrinkage - parallel	1.8	%	ISO 294-4
Mold shrinkage - normal	1.6	%	ISO 294-4
Water absorption (23°C-sat)	0.8	%	ISO 62

Mechanical properties	Value	Unit	Test Standard
Tensile modulus (1mm/min)	2000	MPa	ISO 527-2/1A
Tensile stress at yield (50mm/min)	50	MPa	ISO 527-2/1A
Tensile strain at yield (50mm/min)	12	%	ISO 527-2/1A
Flexural modulus (23°C)	2000	MPa	ISO 178
Charpy impact strength @ 23°C	NB	kJ/m ²	ISO 179/1eU
Charpy impact strength @ -30°C	NB	kJ/m ²	ISO 179/1eU
Charpy notched impact strength @ 23°C	13.0	kJ/m ²	ISO 179/1eA
Charpy notched impact strength @ -30°C	8.0	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
Melting temperature (10°C/min)	166	°C	ISO 11357-1,-2,-3
DTUL @ 1.8 MPa	84	°C	ISO 75-1/-2
DTUL @ 0.45 MPa	148	°C	ISO 75-1/-2
Coeff.of linear therm. expansion (parallel)	1.1	E-4/°C	ISO 11359-2
Coeff.of linear therm. expansion (normal)	1.1	E-4/°C	ISO 11359-2

Test specimen production	Value	Unit	Test Standard
Processing conditions acc. ISO	9988-2	-	Internal

HOSTAFORM® S 9363 XAP²™ | POM | Impact Modified
Typical injection moulding processing conditions

Pre Drying:

Drying is suggested to help achieve low emission performance and to counter if material has contacted moisture through improper storage and handling.

Drying time: 3 h

Drying temperature: 80 - 100 °C

Temperature:

	ϕ Mold	ϕ Melt	ϕ Nozzle	ϕ Zone4	ϕ Zone3	ϕ Zone2	ϕ Zone1
min (°C)	60	180	180	180	180	180	170
max (°C)	70	200	200	200	190	190	180

Pressure:

	Inj press	Hold press	Back pressure
min (bar)	600	600	0
max (bar)	1200	1200	5

Speed:

Injection speed: slow

Special Info:

Do not heat over 205 C (~400 F) to avoid burning and discoloring product.

Contact Information
Americas

8040 Dixie Highway, Florence, KY 41042 USA
 Product Information Service
 t: +1-800-833-4882 t: +1-859-372-3244
 Customer Service
 t: +1-800-526-4960 t: +1-859-372-3214
 e: info-engineeredmaterials-am@celanese.com

Asia

4560 Jinke Road, Zhang Jiang Hi Tech Park

Shanghai 201203 PRC

Customer Service

t: +86 21 3861 9266 f: +86 21 3861 9599

e: info-engineeredmaterials-asia@celanese.com

Europa

Am Unisys-Park 1, 65843 Sulzbach, Germany

Product Information Service

t: +(00)-800-86427-531 t: +49-(0)-69-45009-1011

e: info-engineeredmaterials-eu@celanese.co

HOSTAFORM® S 9363 XAP²™ | POM | Impact Modified

General Disclaimer

This publication was printed based on Celanese's present state of knowledge, and Celanese undertakes no obligation to update it. Because conditions of product use are outside Celanese's control, Celanese makes no warranties, express or implied, and assumes no liability in connection with any use of this information. Nothing herein is intended as a license to operate under or a recommendation to infringe any patents.

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values.

Properties of molded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use.

To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication.

Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards.

We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed (+49 (0) 69 30516299 for Europe, +1 859-372-3244 for the Americas and +86 21 3861 9266 for Asia) for additional technical information. Visit our web site for the appropriate Safety Data Sheets (SDS) before attempting to process our products. Feel free to call Customer Services for additional assistance.

The products mentioned herein are not intended for use in medical or dental implants.

© 2014 Celanese or its affiliates. All rights reserved. (Published 26.September.2014)

Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC.