

LEXAN™ EXL1112T resin

Friday, March 06, 2015

General Information

Product Description

LEXAN® EXL1112T polycarbonate (PC) siloxane copolymer resin is a transparent injection molding (IM) grade. This resin offers good low temperature (-20 C) ductility in combination with high flow characteristics and excellent processability with opportunities for shorter IM cycle times compared to standard PC resins. LEXAN EXL1112T resin is a general purpose product available in transparent and opaque colors.

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific		
Features	• Copolymer • Ductile	• Fast Molding Cycle • Good Processability	• High Flow
Uses	• General Purpose		
Appearance	• Clear/Transparent	• Colors Available	• Opaque
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19		ASTM D792
Density	1.19	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	20	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	1.16	in ³ /10min	ISO 1133
Molding Shrinkage - Flow (0.126 in)	4.0E-3 to 8.0E-3	in/in	Internal Method
Molding Shrinkage - Across Flow (0.126 in)	4.0E-3 to 8.0E-3	in/in	Internal Method
Water Absorption (Saturation, 73°F)	0.12	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	0.090	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ²	328000	psi	ASTM D638
Tensile Modulus	340000	psi	ISO 527-2/1
Tensile Strength ³ (Yield)	8500	psi	ASTM D638
Tensile Stress (Yield)	8380	psi	ISO 527-2/50
Tensile Strength ³ (Break)	8280	psi	ASTM D638
Tensile Stress (Break)	8240	psi	ISO 527-2/50
Tensile Elongation ³ (Yield)	5.7	%	ASTM D638
Tensile Strain (Yield)	5.4	%	ISO 527-2/50
Tensile Elongation ³ (Break)	120	%	ASTM D638
Tensile Strain (Break)	120	%	ISO 527-2/50
Flexural Modulus ⁴ (1.97 in Span)	326000	psi	ASTM D790
Flexural Modulus ⁵	311000	psi	ISO 178
Flexural Stress ^{5, 6}	13000	psi	ISO 178

Disclaimer : THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.

© 2015 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

LEXAN™ EXL1112T resin

SABIC Innovative Plastics Asia Pacific - Polycarbonate

Mechanical	Nominal Value	Unit	Test Method
Flexural Strength ⁴ (Yield, 1.97 in Span)	13700	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁷			ISO 179/1eA
-22°F	21	ft-lb/in ²	
73°F	31	ft-lb/in ²	
Charpy Unnotched Impact Strength ⁷			ISO 179/1eU
-22°F	No Break		
73°F	No Break		
Notched Izod Impact			ASTM D256
-22°F	12	ft-lb/in	
73°F	14	ft-lb/in	
Notched Izod Impact Strength ⁸			ISO 180/1A
-22°F	26	ft-lb/in ²	
73°F	31	ft-lb/in ²	
Unnotched Izod Impact Strength ⁸			ISO 180/1U
-22°F	No Break		
73°F	No Break		
Instrumented Dart Impact (73°F, Total Energy)	663	in-lb	ASTM D3763
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (L-Scale)	89		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi, Unannealed, 0.126 in	251	°F	
Heat Deflection Temperature ⁹			ISO 75-2/Af
264 psi, Unannealed, 2.52 in Span	242	°F	
Vicat Softening Temperature	281	°F	ASTM D1525 ¹⁰
Vicat Softening Temperature			
--	281	°F	ISO 306/B50
--	283	°F	ISO 306/B120
Ball Pressure Test (257°F)	Pass		IEC 60695-10-2
CLTE - Flow (-40 to 203°F)	4.2E-5	in/in/°F	ASTM E831
CLTE - Flow (73 to 176°F)	4.2E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (-40 to 203°F)	4.2E-5	in/in/°F	ASTM E831
CLTE - Transverse (73 to 176°F)	4.2E-5	in/in/°F	ISO 11359-2
RTI Elec	266	°F	UL 746
RTI Str	266	°F	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohm	ASTM D257
Volume Resistivity	> 1.0E+15	ohm·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.0591 in)	HB		UL 94
Glow Wire Flammability Index (0.118 in)	1760	°F	IEC 60695-2-12

Disclaimer : THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.

© 2015 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

LEXAN™ EXL1112T resin

SABIC Innovative Plastics Asia Pacific - Polycarbonate

Flammability	Nominal Value	Unit	Test Method
Glow Wire Ignition Temperature			IEC 60695-2-13
0.0315 in	1560	°F	
0.118 in	1560	°F	
Optical	Nominal Value	Unit	Test Method
Transmittance (100 mil)	82.0	%	ASTM D1003
Haze (100 mil)	3.0	%	ASTM D1003

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	250	°F
Drying Time	3.0 to 4.0	hr
Drying Time, Maximum	48	hr
Suggested Max Moisture	0.020	%
Suggested Shot Size	40 to 60	%
Rear Temperature	423 to 560	°F
Middle Temperature	540 to 580	°F
Front Temperature	560 to 600	°F
Nozzle Temperature	550 to 590	°F
Processing (Melt) Temp	560 to 600	°F
Mold Temperature	160 to 200	°F
Back Pressure	50.0 to 100	psi
Screw Speed	40 to 70	rpm
Vent Depth	1.0E-3 to 3.0E-3	in

Notes

¹ Typical properties: these are not to be construed as specifications.

² 2.0 in/min

³ Type I, 2.0 in/min

⁴ 0.051 in/min

⁵ 0.079 in/min

⁶ Yield

⁷ 80*10*3 sp=62mm

⁸ 80*10*3

⁹ 80*10*4 mm

¹⁰ Rate A (50°C/h), Loading 2 (50 N)

Disclaimer : THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.

© 2015 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.