

NORYL™ GFN3 resin

Friday, March 20, 2015

General Information

Product Description

PPE+PS blend. 30% Glass reinforced. FDA compliance (restrictions apply). Low water absorption. Hydrolytic stability. Dimensional stability. Suitable for fluid engineering applications including pump housings, pump impellers and water meter components.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• Good Dimensional Stability • Hydrolytically Stable • Low to No Water Absorption
Uses	• Engineered Applications • Housings • Pump Parts
Agency Ratings	• FDA Unspecified Rating
Processing Method	• Injection Molding

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31		ASTM D792
Melt Mass-Flow Rate (MFR) (280°C/5.0 kg)	3.2	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (280°C/5.0 kg)	0.165	in ³ /10min	ISO 1133
Molding Shrinkage - Flow (0.126 in)	1.0E-3 to 4.0E-3	in/in	Internal Method
Water Absorption (Saturation, 73°F)	0.10	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	0.040	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ²	1.25E+6	psi	ASTM D638
Tensile Modulus	1.19E+6	psi	ISO 527-2/1
Tensile Strength ³ (Break)	18900	psi	ASTM D638
Tensile Stress (Break)	16000	psi	ISO 527-2/50
Tensile Elongation ³ (Break)	3.0	%	ASTM D638
Tensile Strain (Break)	2.5	%	ISO 527-2/50
Flexural Modulus ⁴ (1.97 in Span)	1.04E+6	psi	ASTM D790
Flexural Modulus ⁵	986000	psi	ISO 178
Flexural Stress ^{5,6}	23200	psi	ISO 178
Flexural Strength ⁴ (Yield, 1.97 in Span)	23200	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁷ (73°F)	3.8	ft-lb/in ²	ISO 179/1eA
Notched Izod Impact			ASTM D256
-22°F	2.2	ft-lb/in	
73°F	1.9	ft-lb/in	

Disclaimer : THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.

© 2015 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

NORYL™ GFN3 resin

SABIC Innovative Plastics Asia Pacific - Polyphenylene Ether + PS

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ⁸			ISO 180/1A
-22°F	4.8	ft·lb/in ²	
73°F	5.2	ft·lb/in ²	
Unnotched Izod Impact (73°F)	11	ft·lb/in	ASTM D4812
Unnotched Izod Impact Strength ⁸ (73°F)	14	ft·lb/in ²	ISO 180/1U
Instrumented Dart Impact (73°F, Total Energy)	177	in·lb	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi, Unannealed, 0.126 in	297	°F	
Deflection Temperature Under Load			ASTM D648
264 psi, Unannealed, 0.126 in	282	°F	
Heat Deflection Temperature ⁹			ISO 75-2/Af
264 psi, Unannealed, 2.52 in Span	282	°F	
Vicat Softening Temperature	297	°F	ASTM D1525 ¹⁰
Vicat Softening Temperature			
--	297	°F	ISO 306/B50
--	300	°F	ISO 306/B120
CLTE - Flow (-40 to 104°F)	1.2E-5	in/in/°F	ASTM E831
CLTE - Flow (-40 to 104°F)	1.3E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (-40 to 104°F)	4.2E-5	in/in/°F	ASTM E831
CLTE - Transverse (-40 to 104°F)	3.9E-5	in/in/°F	ISO 11359-2

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	230 to 250	°F
Drying Time	3.0 to 4.0	hr
Drying Time, Maximum	8.0	hr
Suggested Max Moisture	0.020	%
Suggested Shot Size	30 to 70	%
Rear Temperature	510 to 600	°F
Middle Temperature	530 to 610	°F
Front Temperature	550 to 620	°F
Nozzle Temperature	570 to 620	°F
Processing (Melt) Temp	570 to 620	°F
Mold Temperature	180 to 230	°F
Back Pressure	50.0 to 100	psi
Screw Speed	20 to 100	rpm

Disclaimer : THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.

© 2015 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

NORYL™ GFN3 resin

SABIC Innovative Plastics Asia Pacific - Polyphenylene Ether + PS

Notes

¹ Typical properties: these are not to be construed as specifications.

² 0.20 in/min

³ Type I, 2.0 in/min

⁴ 0.051 in/min

⁵ 0.079 in/min

⁶ Yield

⁷ 80*10*4 sp=62mm

⁸ 80*10*4

⁹ 80*10*4 mm

¹⁰ Rate B (120°C/h), Loading 2 (50 N)

Disclaimer : THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.

© 2015 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.